(19)日本国特許庁 (JP)

(12) 公開特許公報(A)

(11)特許出願公開番号

特開平6-252056

(43)公開日 平成6年(1994)9月9日

(51)Int.Cl. ⁵ H 0 1 L 21/2 21/2 21/0	05 8 B	庁内整理番号 7376-4M	FI				技術表示箇所
		7352-4M	HOIL	21/ 30	3 6 1	P	
			審査請:	求 有	請求項の数 4	OL	(全 4 頁)
(21)出顧番号 特顯平5-35071			(71)出願人		237 気株式会社		
(22)出願日	平成5年(1993)2	月24日		東京都	港区芝五丁目7名	計1号	
			(72)発明者	東京都	港区芝五丁目74	11号	日本電気株
			(74)代理人	式会社 弁理士	おきない。 岩佐 義幸		
		•					
		·					
(54)【発明の名称	】 微細物質の固定な	らびに電極形成法					
	は微細な物質の一部に 固定する、さらに電極		(a) [- -1
を目的とする。		,	r				2 3
	する微細な線状物質2レジスト3中に分散し		(b)				
	線状物質の分散の程度	1					•
	でレジストを感光し明 選んだ材料4を堆積さ		(c)				
質に材料を付着さ	せる。付着させた材料	を適当に選べば		-			
	<u>板を良好に固定すると</u> ものであれば電極を形		(-1)			_	-4
	ば、リフトオフ法によ		(d)				
みを基板上に残す							

(e)

【特許請求の範囲】

【請求項1】微細な線状物質の一部に他の材料を付着さ せたり、微細な線状物質の一部を基板に固定したり、微 細な線状物質の一部に電極を付ける方法において、 前記線状物質を拡散させたレジストを基板上に塗布し、 前記レジストを露光、現像し、

-- 電極または固定用材料を付着する、ことを特徴とする方

【請求項2】微細な線状物質の一部に他の材料を付着さ せたり、微細な線状物質の一部を基板に固定したり、微 10 細な線状物質の一部に電極を付ける方法において、 前記線状物質を拡散させた溶媒を基板上に塗布し、 前記溶媒を蒸発させ、

レジストを塗布し、

前記レジストを露光、現像し、

電極または固定用材料を付着する、ことを特徴とする方 法。

【請求項3】 微細な線状物質の一部に他の材料を付着さ せたり、微細な線状物質の一部を基板に固定したり、微 細な線状物質の一部に電極を付ける方法において、 前記線状物質を拡散させた膜形成用溶液を基板上に塗布 して膜を形成し、

レジストを塗布し、

前記レジストを露光、現像してパターンを形成し、 エッチングにより前記パターンを前記膜に転写し、 電極または固定用材料を付着する、ことを特徴とする方 法。

【請求項4】リフトオフにより前記レジスト上の材料を 除去することを特徴とする請求項1、2または3記載の 方法。

【発明の詳細な説明】

[0001]

【産業上の利用分野】本発明は、微細な物質の一部に他 の材料を付着させ、また基板上に固定し、さらに電極を 形成する方法に関するものである。

[0002]

【従来の技術および解決すべき課題】微細な物質の位置 を固定するためには種々の方法がとられてきた。固定さ れた物質の電気的測定を行うために、物質に電流を流し たり電圧を加えたりするためには電極を取付けなければ 40 ならない。電極の取付法は物質の大きさや性状により種 々の方法がとられている。しかしながら、物質の長さが 数μmもしくはそれ以下に短くなり、太さもマイクロメ ータからナノメートルの大きさとなると、物質の方向や 位置を、その物質を作製した後で制御することは極めて 困難となる。そのため、それらの材料を基板上に固定し 電極を取り付けることははななだ困難となる。

【0003】本発明の目的は、長さや太さが数十µmか ら数nm程度の試料を基板上に密着性良く固定し、さら 形成する方法を提供することにある。

[0004]

【課題を解決するための手段】本発明は、微細な線状物 質の一部に他の材料を付着させたり、微細な線状物質の 一部を基板に固定したり、微細な線状物質の一部に電極 を付ける方法において、前記線状物質を拡散させたレジ ストを基板上に塗布し、前記レジストを露光、現像し、 電極または固定用材料を付着する、ことを特徴とする。

【0005】また本発明は、微細な線状物質の一部に他 の材料を付着させたり、微細な線状物質の一部を基板に 固定したり、微細な線状物質の一部に電極を付ける方法 において、前記線状物質を拡散させた溶媒を基板上に塗 布し、前記溶媒を蒸発させ、レジストを塗布し、前記レ ジストを露光、現像し、電極または固定用材料を付着す る、ことを特徴とする。

【0006】さらに本発明は、微細な線状物質の一部に 他の材料を付着させたり、微細な線状物質の一部を基板 に固定したり、微細な線状物質の一部に電極を付ける方 法において、前記線状物質を拡散させた膜形成用溶液を 20 基板上に塗布して膜を形成し、レジストを塗布し、前記 レジストを露光、現像してパターンを形成し、エッチン グにより前記パターンを前記膜に転写し、電極または固 定用材料を付着する、ことを特徴とする。

[0007]

【作用】本発明においては、物質はレジスト中または溶 媒中または膜形成用溶液中に分散し基板上に塗布され る。溶媒中もしくは膜形成用溶液中に分散させて塗布し た場合は、その後レジストを塗布する。レジスト塗布 後、物質の大きさ、分散の程度に応じて設計したパター 30 ンを露光する。レジストはポジ型でもネガ型でも使用で きる。現像後、物質を基板に固定するための材料を堆積 させる。物質は堆積材料で覆われ基板に固定される。と のとき堆積材料が導体であれば電極となる。必要に応じ てリフトオフすることにより不要な部分の堆積物を取り 除くことができる。

[0008]

【実施例】図1は、物質をレジスト中に分散させる場合 の実施例を説明するための各工程どとの断面図である。 【0009】図1(a)に示すように、まず、基板1を 用意する。基板としては、微細線状物質を固定するだけ の目的の場合には特に種類を選ばない。微細線状物質の 電気測定または光学測定等が必要な場合は、それに応じ て基板の伝導度や光透過係数が最適な基板を選択する。 例えば室温で測定するためには常温で絶縁体のもの、例 えばガラス、半絶縁性半導体基板を用いる。また高周波 特性を測定するためには誘電率の小さい材料、例えばS iO、や雲母などを選択すると良い。光特性も同時に計 測したい場合は、石英その他の材料を用いることができ る。また高温測定する場合にも、石英基板は有効であ に形成が容易なプロセスでかつ接触抵抗の小さい電極を 50 る。低温で電気測定をする場合は、半導体を基板に用い

ることもできる。

【0010】次に、図1(b)に示すように、微細線状 物質2を、レジスト3中に分散し基板1に塗布する。 微 細線状物質としては、電極の形成しにくい微小な材料、 例えばカーボンナノチューブなどを分散させる。レジス ト3は電子ビーム露光用、紫外線露光用などの種類を使 い分ける。レジストは、ポジ、ネガどちらのタイプでも よい。膜厚の均一性が必要な場合は、スピンコーティン グする。その後、レジスト3に必要なプリベーキング等 の分散の程度や方位を測定し、それに併せて固定や電極 付け等に適したパターンを設計する。例えばカーボンナ ノチューブは直径は数nmから数十nmであるが、長さ は1~2μmほどある。そこで、最も簡単なパターンと しては間隔 1 μ m の溝状のパターンを形成し、その溝バ ターンに続けて電極バターンを形成する。

【0011】それらのパターンを、図1(c)に示すよ うに、光露光法や電子ビーム露光法などで露光し、その 後レジスト3を現像する。次に、図1 (d) に示すよう に、目的に応じた材料4を蒸着などで付着させる。材料 20 したくない場合に有効である。 4には、電気測定のためには金、銀、白金、タングステ ン、アルミニウムなどの金属を用いる。材料の付着性が 悪い場合は導伝性高分子などを用いることもできる。固 定のみを目的とする場合は、材料4としてふっ化物、塩 化物などの塩や高分子などを用いることができる。次 に、図1(e)に示すように、リフトオフ法によりレジ スト3を除去することによりレジスト上部の材料4を除 去する。この作業で微細線状物質2の一部に他の材料4 が付着するとともに微細線状物質は基板1に固定され る。材料4として導伝体を用いた場合は、材料は微細線 30 状物質の電極となる。

【0012】図2は、分散媒を用いた場合の実施例を示 す断面図である。分散媒としては、アルコール、アセト ンなどを用いることができる。まず図2(a) に示すよ うに、基板 1 を用意し、次に図2(b)に示すように、 微細線状物質2をアルコールなどに分散し基板1に塗布 する。 微細線状物質 2 が適当な間隔で基板 1 上に残り、 分散媒は蒸発してなくなる。その後図2(c)に示すよ うに、レジスト3を塗布し、続いて図1において説明し たようにパターンを形成する。次に図2(d)に示すよ 40 4 電極または固定用材料

に、材料4を付着させる。最後に図2(f)に示すよう に、リフトオフにより微細線状物質2を基板1上に固定 し、または電極を作製することができる。

【0013】図3は、膜形成用溶液に物質を分散させて 基板上に塗布する実施例を説明するための断面図であ

【0014】まず図3(a)に示すように、基板1を用 意し、続いて図3(b)に示すように、微細線状物質2 の処理を施す。レジストを塗布した後の微細線状物質2 10 を分散させた膜形成用ポリイミドの溶液を塗布し、膜5 を形成する。次に図3(c), (d)に示すように、膜 5上にレジスト3を塗布し、露光、現像してパターンを 形成する。続いて図3(e)に示すように、レジスト3 に形成したパターンをエッチングより下層の膜5に転写 する。次に図3(f)に示すように、材料4を付着させ る。最後に図3(g)に示すように、リフトオフによ り、膜5 および膜5上のレジストを除去し、試料2を基 板1上に固定しまたは電極を作製することができる。と の2層膜法は露光時に電子ビームや紫外線を膜5に照射

[0015]


【発明の効果】本発明により極微細な試料、例えばカー ボンナノチューブを容易に基板上に固定することができ る。さらに付着する材料および基板を適当に選べば電極 作製が行え、電気測定や光学的測定が行える。本発明の 方法は従来の半導体製造プロセスと互換性がある。よっ て、極微細な構造物の電気的、光学的に特異な物性を電 子デバイスとして利用するための基本構造にもなる。

【図面の簡単な説明】

- 【図1】本発明の一実施例を示す工程ととの断面図であ
 - 【図2】本発明の一実施例を示す工程ととの断面図であ
 - 【図3】本発明の一実施例を示す工程ととの断面図であ る.

【符号の説明】

- 1 基板
- 2 微細線状物質
- 3 レジスト



(a) [図2]
(b) 2
(c) 3
(d) (e) 4

Japanese Open-Laid Publication Number: 06-252056

Date of publication of application: 09.Sep.1994

Application number: 05-035071

Date of filing: 24.Feb.1993

Applicant: Nippon Electric Corporation (NEC)

Inventor: Yukinori OCHIAI

Representative: Patent Attorney Yoshiyuki IWASA

Title of the Invention: FIXATION OF MINUTE SUBSTANCE AND

FORMATION OF ELECTRODE

[ABSTRACT]

[PURPOSE] To attach another material on a part of minute substance and to fix it on a substrate and further to form an electrode.

[CONSTITUTION] A minute linear substance 2 as an object, for example, carbon nanotubes are dispersed in a resist 3 and spread over a substrate1. Next, the resist is exposed to light by using a pattern which is designed according to degree or orientation of dispersion of the minute linear substance and then developed. After that, a material 4 selected according to the need is deposited and attached to the minute linear substance. If the attached material is selected properly, the minute linear substance can be well fixed to the substrate. Also, if the material is conductive, electrode can be formed. If necessary, only a sample and the material can be left on the substrate by lift-off method.

[CLAIMS]

[Claim 1] In a method of adhereing another material to a part of minute linear substance, fixing a part of minute linear substance on a substrate, or attaching an electrode to a part of minute linear substance, said method characterized by applying a resist diffused said minute linear substances on said substrate, exposing and developing said resist, and attaching said electrode or an anchoring material.

[Claim2] In a method of adhering another material to a part of minute linear substance, fixing a part of minute linear substance on a substrate, or attaching an electrode to a part of minute linear substance, said method characterized by applying a solvent diffused said minute linear substances on said substrate, evaporating said solvent, applying a resist, exposing and developing said resist, and attaching said electrode or an anchoring material.

[Claim3] In a method of adhering another material to a part of minute linear substance, fixing a part of minute linear substance on a substrate, or attaching an electrode to a part of minute linear substance, said method characterized by applying a film forming solution diffused said minute linear substances on a substrate to form a film, applying a resist, exposing said resist, forming a pattern by developing, transcribing said pattern on said film by etching, and attaching said electrode or an anchoring material.

[Claim4] The method according to claim 1, 2 or 3, wherein said material on said resist is removed by lift-off method.

[Detailed Description of the Invention]

[0001]

[Industrial Application] The present invention relates to a method of adhering another material to a part of minute substance, fixing a part of said minute substance on a substrate, and further forming an electrode.

[0002]

[Prior Art and Problem to be solved] Various methods have been used to fix the location of minute substance. In order to perform the electric measurement of the fixed material, an electrode must be attached to flow a current to said material or to apply voltage to said material. Various methods depending on the size and shape of said material are used to attach the electrode. However, in the case that the length of the material is several micro meters (µm) or shorter and its thickness is micrometer order to nanometer order, it is quite difficult to control the direction and location of the material after producing said material. Therefore, it becomes quite difficult to fix the material on a substrate and to attach an electrode.

[0003] The purpose of the present invention is to present a method for fixing a sample having several tens of µm to several nm in length and thickness on a substrate fitly and further for forming a small electrode with small contact resistance by easy forming processes.

[0004]

[Means for Solving the Problem] The present invention is characterized in that, in a method of adhering another material to a part of minute linear substance, fixing a part of minute linear substance on a substrate, or attaching an electrode to a part of minute linear substance, such method comprises the steps of

applying a resist diffused said minute linear substances on a substance, exposing and developing said resist, and attaching an electrode or an anchoring material.

[0005] In addition, the present invention is characterized in that, in a method of adhering another material to a part of minute linear substance, fixing a part of minute linear substance on a substrate, or attaching an electrode to a part of minute linear substance, said method comprises the steps of applying a solvent diffused said minute linear substances on said substrate, evaporating said solvent, applying a resist, exposing and developing said resist, and attaching said electrode or an anchoring material.

[0006] Furthermore, the present invention is characterized in that, in a method of adhering another material to a part of minute linear substance, fixing a part of minute linear substance on a substrate, or attaching an electrode to a part of minute linear substance, said method comprises the steps of applying a film forming solution diffused said minute linear substances on a substrate to form a film, applying a resist, exposing said resist, transcribing a pattern by developing, forming said pattern on said film by etching, and attaching said an electrode or an anchoring material.

[0007]

[Function] In the present invention, said material is dispersed in said resist, solvent or film forming solution, and is applied on the substrate. If said material is dispersed in the solvent or film forming solution and is applied, the resist is applied after that. After applying said resist, there is exposed a designed pattern depending on the size of the material and degree of said dispersion. A negative type or positive type can be used as said resist. After

development, said material to adhere said material on said substrate is deposited on said substrate. Said material is covered with the deposition material to be fixed. If said deposition material is conductor, it becomes electrode.

Depending on necessity, the deposition material on the undersigned portion can be removed by lift-off method.

[0008]

[Embodiment] Fig. 1 is a cross sectional view at each process to explain the embodiment to disperse the material in the resist.

[0009] As shown in the Fig. 1(a), substrate 1 is prepared. Any type of substrate can be available for the purpose of only fixing minute linear substance. If electrical measurement or optical measurement etc. is needed, the optimum substrate on light transmission coefficient and good conductivity is selected depending on the condition. For example, to measure at room temperature, the materials being insulator at ordinary temperature, for example a glass or semi-insulating semiconductor substrate is used. For example, SiO2 or mica having small dielectric constant is preferable for measurement of high frequency Quartz or other materials can be used in the case that optical property is also measured at the same time. Furthermore, in the case of pyrometry, quarts substrate is preferable. In the case of electrical measurement at low temperature, semiconductor can be used as a substrate.

[0010] Next, as shown in Fig. 1(b), minute linear substance 2 is dispersed in resist 3 and is applied to substrate 1. As said minute linear substance, for example, carbon nanotube etc. which do not form electrode with ease is dispersed. Said resist 3 is chosen property for electron beam exposure, ultraviolet-rays

exposure and so on. A positive or negative type is available for the resist. In the case that uniformity of the film thickness is needed, spin coating is carried out. After that, said resist 3 is pre-baked etc. if necessary. After the resist is applied, the degree of dispersion of minute linear substance 2 and its direction are measured and depending on the conditions, the pattern suitable for fixation and electrode attachment is designed. For example, carbon nanotube has a few nm to several tens of nm in diameter and 1 to 2 µm in length. Thus, the groove-like pattern with 1 µm interval is formed as the most simple pattern and the electrode pattern is formed next to the groove-like pattern.

[0011] As shown in Fig. 1(c), said pattern is exposed by optical exposure method or electron beam exposure method etc. and then, said resist 3 is developed. Next, as shown in Fig. 1(d), the material 4 according to the purpose is adhered by vapor deposition etc. In the case of electric measurement, metal of gold, silver, platinum, tungsten or aluminum etc. is used for the material 4. A conductive macromolecule etc. can be used if the material cannot adhere well. If the purpose is only fixing, fluoride and salt such as chloride, and macromolecule etc. can be used as material 4. Next, as shown in Fig. 1(e), the material 4 of the upper part of said resist is removed by removing said resist 3 by lift-off method. While other material 4 adheres to a part of minute linear substance 2, minute linear substance is fixed to said substrate 1 by this operation. Said material becomes electrode of minute linear substance if conductor is used as the material 4.

[0012] Fig. 2 is a cross sectional view showing the embodiment of the case that disperse medium is used. Alcohol and acetone etc. can be used as said disperse medium. First, as shown in Fig. 2(a), substrate 1 is prepared, and next,

as shown in Fig. 2(b), minute linear substance 2 is dispersed in alcohol etc, and it is applied to the substrate 1. Said minute linear substance 2 remains on the substrate 1 with appropriate interval, and the disperse medium evaporates away. After that, as shown in Fig. 2(c), the resist 3 is applied and the pattern is formed as described in the case of Fig. 1. Then, exposure and development are performed as shown in Fig. 2(d), and successively the material 4 is adhered as shown in Fig. 2(e). Finally, as shown in Fig. 2(f), the minute linear substance 2 is fixed on the substrate 1 by lift-off method, and as a result the electrode is formed.

[0013] Fig. 3 is a cross sectional view to explain an embodiment of dispersing the material in the film forming solution and applying the solution to the substrate.

[0014] First, as shown in Fig. 3(a), substrate 1 is prepared, and continuously, solution of polyimide dispersed minute linear substance is applied to form the film 5 as shown in Fig. 3(b). Next, as shown in Fig. 3(c) and 3(d), the resist 3 is applied on said film 5, and the pattern is formed by exposing and developing. And then, as shown in Fig. 3(e), said pattern formed on said resist 3 is transcribed on lower layer film 5 by etching. Next, material 4 is adhered as shown in Fig. 3(f). Finally, as shown in Fig. 3(g), film 5 and resist on said film 5 are removed by lift-off method, and the material 2 is fixed on substrate 1 and an electrode can be produced. This two-layer-film method is efficient in the case that the if film 5 must not irradiated by electron beam or ultraviolet ray when exposing.

[0015]

for example carbon nanotube, can be fixed on a substrate with ease.

Furthermore, if suitable material to be adhered and substrate are chosen

appropriately, an electrode can be produced, and electric measurement and

optical measurement can be performed. The present invention method is

compatible with conventional process of semiconductor production. Therefore,

the present invention provides a basic structure of ultrafine construction to utilize

the electrical and optical peculiarity as electric device.

[Brief Description of Drawings]

[Figure 1] A cross sectional view to explain the process showing an embodiment of the present invention.


[Figure 2] A cross sectional view to explain the process showing an embodiment of the present invention.

[Figure 3] A cross sectional view to explain the process showing an embodiment of the present invention.


[Description of Notations]

- 1 substrate
- 2 minute linear substance
- 3 resist
- 4 electrode or anchoring material


[Fig.1]



[Fig.2]



[Fig.3]



This Page is Inserted by IFW Indexing and Scanning Operations and is not part of the Official Record

BEST AVAILABLE IMAGES

Defective images within this document are accurate representations of the original documents submitted by the applicant.

Defects in the images include but are not limited to the items checked:
☐ BLACK BORDERS
☐ IMAGE CUT OFF AT TOP, BOTTOM OR SIDES
☐ FADED TEXT OR DRAWING
BLURRED OR ILLEGIBLE TEXT OR DRAWING
☐ SKEWED/SLANTED IMAGES
COLOR OR BLACK AND WHITE PHOTOGRAPHS
☐ GRAY SCALE DOCUMENTS
☐ LINES OR MARKS ON ORIGINAL DOCUMENT
☐ REFERENCE(S) OR EXHIBIT(S) SUBMITTED ARE POOR QUALITY

IMAGES ARE BEST AVAILABLE COPY.

As rescanning these documents will not correct the image problems checked, please do not report these problems to the IFW Image Problem Mailbox.